

Specification for Approval

緯創料號

Wistron Part No. : 86.5A534.5R0

Description : SCRW FLAT M3*5

廠商型號


Vendor Model No. :

Descriptio: SCRW FLAT M3*5

Issued Date : 2005/02/14

Approved Date : 2005/02/17

Approved by (Wistron)	Approved by (vendor)	Prepared by (vendor)
勞武 2005/02/17	Xueling.Liu 2005/02/14	Liang Fang 2005/02/14



FAI DATA SHEET

[illegible]

Wen Yih Plastic/Screws Hardware Factory

SALT SPRAY TEST REPORT

CUSTOMER	<i>WISTRON</i>	DESCRIPTION	M3*5FM	TEST QUANTITY	10 PCS
C-PART NO	86.5A534.5R0	PLATING	NI	NACL percentage	5%
DATE	2005.02.14	INSTRUMENT	SALT SPRAY TESTER	PLACE	Laboratory
TIME: 8:00 <u>14-FEB</u> To 16:00 <u>14-FEB</u> Total <u>8</u> hours					
The reason when interrupt testing is: _____					
ITEM		CONDITION		RESULT	
Fog speed quantity		1.0~2.0ml/80cm2/n		1.7	
PH Amount		6.5~7.2		6.8	
Air-pressure torque		0.9~1.1kg/cm2		1.0	
Laboratory humidity		85%(min)		86	
Laboratory temperature		34℃~36℃		35	
Pressure-tub temperature		46℃~48℃		47	
Salt-water temperature		34℃~36℃		35	
Others					
Test result → According to JIS H 8502 standard chart judge: <u>7</u> Grade. ★ accept ☆ reject					
Remark:					

REV:Xueling.Liu

INS : *Liang Fang*

文益塑膠五金廠

扭力測試報告表

客戶名稱	偉創	測試條件	孔徑	<input type="checkbox"/> 6#-32標準孔 <input checked="" type="checkbox"/> M3*0.5標準牙孔 <input type="checkbox"/> M3.5牙孔 <input type="checkbox"/> M4標準牙孔 <input type="checkbox"/> 直徑6.10±0.10mm <input type="checkbox"/> 直徑7.10±0.05mm <input type="checkbox"/> 直徑5.40±0.05 mm/-0.01mm <input type="checkbox"/> 直徑6.60±0.10mm <input type="checkbox"/> 直徑2.80±0.05mm <input type="checkbox"/> 直徑5.40±0.10mm								
品名	螺絲											
料號												
規格	3*5FM											
批量												
抽樣數	10PCS	測試工具	<input checked="" type="checkbox"/> 壹式虎鉗 <input checked="" type="checkbox"/> 電動起子 <input checked="" type="checkbox"/> 孔徑實配板 <input checked="" type="checkbox"/> 扭力計 <input type="checkbox"/> 其他									
OK判定極限值		螺絲扭力	<input type="checkbox"/> f 大于或等於10kgf <input checked="" type="checkbox"/> f 大于或等於12kgf <input type="checkbox"/> f 大于或等於15kgf									
測試值	序號	判定	1	2	3	4	5	6	7	8	9	10
10kgf	10kgf											
	11kgf											
	12kgf								OK			
	13kgf	OK		OK		OK	OK		OK	OK	OK	
	14kgf		OK		OK							
12kgf	12kgf											
	13kgf											
	14kgf											
	15kgf											
	16kgf											
OK測試 極限值	kgf											
	kgf											
判定	<input checked="" type="checkbox"/> 合格 <input type="checkbox"/> 不合格 <input type="checkbox"/> 其它											
備注	1. 測試記錄中判定以"ok"為標準。											
	2. 測試值不限小於"ok"測試值,應根據測試值測試相關數據作判定。											
	3. 當超過標準值測試"ok"時,應記錄於"ok"測試極限值欄中,並記錄測試數值,以便追蹤。											

審核: 江瑞祥

測試: 袁瑞誠

Chlorine

TEST CERTIFICATE

中國鋼鐵股份有限公司
CHINA STEEL CORPORATION
中華民國高雄市小港區中興路1號
CHUNG KANG ROAD HSIAO KANG, KAOHSIUNG
TAIWAN, REPUBLIC OF CHINA
TEL: (07)802-1111 FAX: (07)802-2511, (07)804-9427

80008-01 0623

<p>SUPPLY TO</p>	<p>茲證明本表所列產品，均按材料規格製造及試驗，並符合規格之要求。 WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.</p>	<p>YCHuang for 冶金技術處處長</p>
------------------	---	---